

# KLINGERSIL<sup>®</sup>, KLINGER<sup>®</sup> TOP-SIL, KLINGER<sup>®</sup> QUANTUM COMPRESSED FIBER REINFORCED MATERIAL

## Storage and Shelf Life

Compressed non-asbestos gasket materials are, like all elastomer-containing materials, subject to a natural aging process. This process depends on the kind of elastomer, its vulcanization system, and the storage conditions. Unfavorable storage conditions such as extreme temperatures, exposure to sunlight, low humidity, etc. can lead to a premature reduction of the material's quality. However, the following conditions for proper storage should be followed in order to achieve an optimum shelf life of 5 years:

- » Temperature <77°F (25°C)
- » Relative humidity between 50-60%
- » No exposure to direct sunlight or other intensive light source
- » No contact with metals
- » Store horizontally (flat) on a shelf/rack

*The ability of a gasket to make and maintain a seal depends not only on the style and quality of the gasket material, but also on medium being sealed, the flange design, the amount of pressure applied to the gasket by the bolts and how the gasket is assembled onto the flanges and tightened. These factors are beyond the manufacturer's control.*

**KLINGER Thermoseal**

2350 Campbell Road, Sidney, Ohio 45365  
Tel: +1 937 498 2222

3803 S. Sam Houston Parkway W., Houston, Texas 77053  
Tel: +1 713 997 8111